

General Description

A first quality natural base asphalt cutback that is filled and fibrated to give good adhesion and a strong flexible film that resists chemical attack. May be supplied with integral aluminum pigment.

Uses

It is a protective coating for steel tanks, pipes, ships, structural steel, concrete or thermal insulation.

Limitations

The dry coating will redissolve in petroleum solvents.

Physical Properties

Colour	- Black
Weight	- 1 kg per litre or 10 lbs. Per gallon
Theoretical Coverage	- 960 square feet per gallon per mil.
Practical Coverage	- 4 L per square meter @ 3mm dry or 7 – 10 U.S. gallons per 100 Square feet for 1/8 " dry
Dry Time	- at 50 % R.H., 21 deg C Dry to touch: 12 hours Dry to Firm: 72 hours
Service Temperature	- 40 to 120 deg C (-40 to 250 deg F)
Shelf Life	- Up to 12 months
Flash point	- 38 deg C (100 deg F)

Preparatory Work

Surfaces to be coated should be cleaned to remove all dirt and rust. If there is a delay between cleaning and application, steel surfaces should be primed with I-M 7510.

Precautions

This product is flammable and must be kept away from open flames. There is a strong solvent odour so ventilation is important. Harmful if swallowed.

Work Characteristics

9805 will not freeze but warming is necessary in cold weather to reduce viscosity.

Installation Instructions

Applied with a trowel or spray gun to give a uniform coating to the surface. Mineral Spirits can be used for clean up.