

General Description

A thixotropic solvent based rust preventative that provides superior performance in combating vehicular rust. It can be applied with standard airless, atomization spray equipment with a minimum of overspray while coating metal surfaces.

Performance

9822's unique molecular action prevents rust before it starts and kills rust after it starts. 9822 Rustproofing's penetrating and rust protective properties start working immediately upon application to cars, trucks, boats, industrial equipment, farm machinery etc.

Physical Properties

Recommended film thickness: approx. 10 mil

Preparatory Work

Surfaces should be prepared by removing dirt, loose scaly rust and any other foreign substances that would reduce the coatings adhesion. Enclosed areas and boxed sections should be checked for entry ports. Typically application is made with airless, atomization spray equipment using 45 to 60 psi nozzle pressure. Spray tips with approximately 0.13 inch orifice size is recommended. A cone pattern rather than a flat pattern may be preferred.

Application Procedure

Do not coat the exhaust system or body parts near the exhaust system.

Caution

9822 should be handled with the same care as used when spraying solvent based paints in enclosed areas. Avoid skin contact and excessive breathing of solvent vapours. Solvent used is mostly mineral spirits. The applicator should wear an approved respirator and safety glasses, clothing and gloves should be solvent resistant. Consult Material Safety Data Sheet.