

## General Description

7501 is a solvent solution of SBS polymer modified asphalt. It is a quality penetrating primer of thin brush or spray consistency that exceeds CGSB 37-GP-9Ma.

## Uses

Its main use is for priming absorbent surfaces to improve the bond and provide a tack coat for the application of modified asphalt coatings, sheet membranes, and thermally fused membranes.

## Limitations

This is a flammable product and care must be taken to keep away from open flames and provide ventilation to remove fumes. It should not be stored at temperatures in excess of 50°C or 120 °F.

## Physical Properties

Colour	- Black
Solids	- 36.5 % minimum
Drying Time	- Touch dry- 30 min at 25°C (77°F) Firm dry - 2 hours at 25°C (77°F)
Density	- 0.91 kg per litre (7.5 lb. Per U.S. gallon)

## Preparation

Surfaces should be clean, dry and scraped clean of gravel dirt and rough projections.

## Characteristics

It is a thin solution and will not freeze. It is applied at a rate of 2.4 to 3.7 litres per 10 square meters (1/2 to 1 gallon per 100 square feet).

## Application

Roofs - Apply by brush, roller, spray at a rate of 1 litre per 3.5 sq. metres (3/4 gal/100 sq.ft.). Use adequate amount without pooling. Let primer dry before applying asphalt topcoat.  
Foundations - Apply by brush, roller or spray at a minimum rate of 0.4 litres per square meter (1gal/100sq.ft.).