

General Description

A highly penetrating, self -healing resaturant for maintaining dead level or low slope roofs. Roof Resaturant 7520 is a fibrated asphalt cutback with special penetrating oils that migrate into oxidized asphalt films and felts to restore pliability.

Uses

Resaturating old, weathered, dead level or low slope asphalt membrane.

Physical Properties

Colour	-	Black
Weight per Litre	-	1.01 kg approximately
Drying Time	-	Because of the penetrating oils it will remain tacky for an indefinite period of time.

Precautions

Do not use over coal tar pitch coatings. Do not use on metal roofs or on roofs with a slope more than 17 cm per metre or 2 inches per foot.

Preparation

Remove all loose gravel and all dirt. Surface must be sound and free from moisture or frost. Repair cracks, holes or leaking overlaps with 7509, Plastic Cement and fiberglass, polyester or other membrane. Let patches cure overnight.

Application

Apply 7520 Resaturant uniformly by spray, brush or squeegee. On old, weathered dead level roofs use approximately 2.5 - 3 litres per square meter (6 – 7 U.S. gallons per 100 square feet). With slopes around 17 cm per meter or 2 inches per foot, or if roof is not badly weathered, use approximately 2 litres per square meter or 5 U.S. gallons per 100 square feet. Apply clean gravel or stone at approximately 24 kg per square meter (500 lbs per 100 square feet).

Clean Up

Use Mineral Spirits

Caution

Keep away from open flame or spark. Keep out of reach of children.

First Aid

Contains petroleum distillate and mineral fillers. If swallowed, do not induce vomiting. Call a physician immediately.