

General Description

A premium quality natural base asphalt cutback blended with selected gilsonites for added strength and heat stability.

Uses

Used as a primer on wood and metal surfaces prior to the application of 9812 Black Fibered Kiln Coating.

Limitations

The surface to be coated must be clean and dry. Apply at above 5°C or 40°F.

Physical Properties

Colour	-	Black
Density	-	0.91 kg per litre or 7.6 lb. per gallon
Dry to Touch	-	1 hour at 77°F
Dry to Hard	-	24 hours
Temperature Resistance	-	-40 to 120°C (-40 to 250°F)
Practical Coverage	-	2 – 6 square meters per litre (80-250 sq.ft. per US gallon)

Preparatory Work

Surfaces to be coated should be cleaned with sand, water or air blast to remove all dirt and wood resin build up. Cracks or holes should be repaired with 9805 Protective Mastic. Surfaces should be primed with 9811 Black kiln Coating Primer. Allow primer to dry tack free before applying 9812.

Precautions

9811 contains petroleum solvents. Maintain good ventilation and keep away from sparks or open flame. Harmful if swallowed.

Installation Instructions

Stir the coating before the application. Apply by spray (mastic spray equipment) or brush. For clean up use petroleum solvents.