

General Description

A premium quality asphalt emulsion blend. 9811WB has good adhesion and forms a strong flexible protective film that resists attack.

Uses

A preservative coating for protecting the interior structure of wood drying kilns from the corrosive action of wood resins.

Limitations

The surface to be coated must be clean and dry. Apply at above 4 °C.

Physical Properties

Practical Coverage	125 sq. feet per US gal (3 sq. meter/litre)
Dry to Touch	30 – 45 at 77°F
Dry to Hard	12– 24 hours at 77°F
Colour	Black
Dry Film Temperature Resistance	-40 deg. F to 240 deg.F
Density	9.31 lbs/US gal.

Preparatory

Surfaces to be coated should be sand blasted to remove all dirt and wood resin build up. Cracks or holes should be repaired with 9805 Protective Mastic and allowed to cure (minimum 48 hrs.) Surfaces should be sprayed with an airless sprayer or rolled to recommended coverage. Clean up with water while wet or Mineral Spirits if dry.

Caution

9811WB cannot be applied below 40° F (4°C) as it freezes and is damaged by freezing.