

General Description

A premium quality asphalt and gilsonite cutback blend. 9812 is fibered and has good adhesion and forms a strong flexible protective film that resists attack.

Uses

A preservative coating for protecting the interior structure of wood drying kilns from the corrosive action of wood resins.

Limitations

The surface to be coated must be clean and dry. Apply at above 5^oC.

Physical Properties

Colour	-	Black
Weight	-	1.04 kg per litre (10.5 lbs/gal)
Dry to touch	-	6 hours at 25 ^o C (77 ^o F)
Dry to hard	-	48 hours at 25 ^o C (77 ^o F)
Temperature Resistance	-	-40 to 120 ^o C
Practical Coverage	-	60 square feet per gallon (1.2 square meters per litre)

Preparatory

Surfaces to be coated should be sand blasted to remove all dirt and wood resin build up. Cracks or holes should be repaired with 9805 Protective Mastic. Surfaces should be primed with 9811 Black Kiln Coating Primer. Allow primer to dry tack free before applying 9812.

Installation Instructions

Stir the coating before the application. Apply by spray (mastic spray equipment) or brush. If thinning is required, use 9811 Kiln Coating Primer. For clean up use petroleum solvents.