

### General Description

A durable asphalt cutback underbody coating for cars and trucks, It is a tough fibre reinforced material that is carefully blended for use with an airless undercoater pump.

### Uses

9819 Undercoating will prevent rust and corrosion, deaden sound, insulate against heat and cold, dust proof and seal against water leaks.

### Physical Properties

Theoretical Coverage : 1,520 square feet per gallon per mil.  
Practical Coverage : 150 square feet per gallon  
Dry to Touch : 4 to 6 hours at 77 deg F  
Dry to Hard : 24 hours at 77 deg F  
Colour : Black  
Temperature Resistance : -40 deg F to 80 deg F  
Weight per Gallon : 10.9 lbs.  
Flash point : 43 Deg C - T.C.C.

### Preparatory Work

Dirt and dust should be cleaned from the underbody before application. To remove caked on dirt, steam cleaning is recommended. Surface should then be thoroughly dry before application.

### Application

9819 is best applied with a 15 to 1 ratio Graco Airless Undercoater Pump Model #226-343 or equal, having a reversible nozzle with a tip opening of between .024 - .027 inches. Best results are obtained when the nozzle is held 12 inches away from the surface to be sprayed and perpendicular to it. The viscosity of the material increases at lower temperatures. Clean tools and equipment with Mineral Spirits.

### Caution

Contains petroleum solvents. Take suitable fire precautions. Use in well ventilated areas. Keep containers covered when not in use.