

General Description

7501 is a solvent solution of refined natural asphalt. 7501 is a quality, penetrating primer of thin brush or spray consistency that conforms to 37-GP-9Ma and ASTM D41(Type II).

Uses

Its main use is for priming absorbent surfaces to improve the bond and provide a tack coat for the asphalt coating to be applied. 7501 may be used to prime and revitalize dried out asphalt roofing felts before recoating with asphalt roof coatings such as 7502, 7504 or 7506.

Limitations

This is a flammable product and care must be taken to keep away from open flames and provide ventilation to remove fumes. Do not store at temperatures more than 50°C or 120°F. When used as a primer for asphalt emulsion coatings, such as 7101 or 7502, allow to cure at least 12 hours before over coating. Do not apply to wet or frosted surfaces.

Physical Properties

Colour	- Black
Solids	- 56 % minimum
Drying Time	- Touch dry- 1 hour @ 25°C (77°F) Firm dry - 12 hours at 25 ° C (77°F)
Density	- 0.89 kg per litre (7.4 lb. Per U.S. gallon)

Preparation

Surfaces should be clean, dry and scraped clean of gravel dirt and rough projections. Repair cracks or holes with asphalt plastic cement, 7509.

Characteristic

It is a thin solution and will not freeze. It is applied at a rate of 2.4 to 3.7 litres per 10 square meters (1/2 to 1 gallon per 100 square feet).

Application

Roofs - Apply by brush, roller spray at a rate of 1/4 to 1 litre per square meter. Use adequate amount without pooling. Let primer dry before applying asphalt topcoat.
Foundations - Apply brush, roller or spray at a minimum rate of 0.4 litres per square meter. Topcoat with 7102 at a minimum rate of 0.6 litre per square meter.